

물 성 표



| | |
|----------------|--------------------|
| PC | 제 품 특 성 |
| PRODUCT/ GRADE | 우수한 이형성, 중점도 GRADE |
| DPC-510 | |

| Property | Test Method | Test condition | Unit | Result |
|---|-------------|---|--------------------|---------|
| SPECIFIC GRAVITY(비중) | ASTM D792 | | | 1.20 |
| Mold Shrinkage (성형수축율) | ASTM D955 | | % | 0.5~0.7 |
| Melt Flow Rate(유동성) | ASTM D1238 | 300°C X 1.2kg | g/10min | 8.0 |
| | | | | |
| Tensile Strength(인장강도) | ASTM D638 | 50mm/min | kg/cm ² | 680 |
| Tensile Modulus(인장탄성율) | ASTM D638 | 1mm/min | kg/cm ² | |
| Elongation at Yield(신율) | ASTM D638 | 50mm/min | % | |
| Flexural Strength(굴곡강도) | ASTM D790 | 15mm/min | kg/cm ² | 950 |
| Flexural Modulus(굴곡 탄성율) | ASTM D790 | 15mm/min | kg/cm ² | 22,000 |
| IZOD IMPACT(충격강도) | ASTM D256 | 1/4", 23°C | kg·cm/cm | 75 |
| | | 1/4", -30°C | kg·cm/cm | |
| | | 1/8", 23°C | kg·cm/cm | |
| | | 1/8", -30°C | kg·cm/cm | |
| Rockwell hardness | ASTM D785 | R-Scale | | |
| Heat Deflection Temperature (열변형 온도) | ASTM D648 | 18.6kg/cm ² 1/4" (Annealed) | °C | 125 |
| | | 18.6kg/cm ² 1/4" (Unannealed) | °C | |
| | | 4.6kg/cm ² 1/4" (Annealed) | °C | |
| | | 4.6kg/cm ² 1/4" (Unannealed) | °C | |
| Vicat Softening Temp (annealed)(Vicat 연화점) | ASTM D1525 | 5kg/50°C/h | °C | 140 |
| Flammability(난연성) | UL94 | 1/8" | class | V-2 |
| Chatacteristics(특성) | | | High Impact(내충격) | |

DREAM Chem Co., Ltd



#121 SAMGYE-GIL CHEONGBUK-MYEON

PYEONGTAEK-SI GYEONGGI-DO 451-832 KOREA

www.dreamchem.net

Tel : 82-31-684-9002, Fax : 82-31-684-9022