

물 성 표



PC	제 품 특 성
PRODUCT/ GRADE	우수한 이형성, 중점도 GRADE
DPC-515	

Property	Test Method	Test condition	Unit	Result
SPECIFIC GRAVITY(비중)	ASTM D792			1.20
Mold Shrinkage (성형수축율)	ASTM D955		%	0.5~0.7
Melt Flow Rate(유동성)	ASTM D1238	300°C X 1.2kg	g/10min	15.0
Tensile Strength(인장강도)	ASTM D638	50mm/min	kg/cm ²	700
Tensile Modulus(인장탄성율)	ASTM D638	1mm/min	kg/cm ²	
Elongation at Yield(신율)	ASTM D638	50mm/min	%	
Flexural Strength(굴곡강도)	ASTM D790	15mm/min	kg/cm ²	950
Flexural Modulus(굴곡 탄성율)	ASTM D790	15mm/min	kg/cm ²	24,000
IZOD IMPACT(충격강도)	ASTM D256	1/4", 23°C	kg·cm/cm	75
		1/4", -30°C	kg·cm/cm	
		1/8", 23°C	kg·cm/cm	
		1/8", -30°C	kg·cm/cm	
Rockwell hardness	ASTM D785	R-Scale		
Heat Deflection Temperature (열변형 온도)	ASTM D648	18.6kg/cm ² 1/4" (Annealed)	°C	125
		18.6kg/cm ² 1/4" (Unannealed)	°C	
		4.6kg/cm ² 1/4" (Annealed)	°C	
		4.6kg/cm ² 1/4" (Unannealed)	°C	
Vicat Softening Temp (annealed)(Vicat 연화점)	ASTM D1525	5kg/50°C/h	°C	140
Flammability(난연성)	UL94	1/8"	class	V-2
Chatacteristics(특성)			High Impact(내충격)	

DREAM Chem Co., Ltd



#121 SAMGYE-GIL CHEONGBUK-MYEON

PYEONGTAEK-SI GYEONGGI-DO 451-832 KOREA

www.dreamchem.net

Tel : 82-31-684-9002, Fax : 82-31-684-9022